

Novagard® 800 Series 800-620
UV Cure Silicone
Specification Data



DESCRIPTION

Novagard 800 Series 800-620 is a UV curable silicone gel. This non-corrosive, single component silicone will cure to a solid elastomer in seconds upon exposure to ultraviolet (UV) light.

APPLICATIONS

- Printed circuit/wiring boards
- Flexible hybrid electronics
- Rigid electronics
- Sensitive components and harsh environments
- Potting

FEATURES & BENEFITS

- Electronics grade
- Exceptionally fast cure
- Room temperature cure
- Single component
- No oxygen inhibition
- 100% solids
- No solvents
- Non-corrosive, neutral cure
- Enhances reliability of delicate components
- Provides stress and shock relief
- Temperature stable from -40°C to 200°C

APPLICATION METHOD

Novagard 800 Series 800-620 can be applied by automated needle dispense, hand dispense, flow coating, or hand brushing.

UV CURE CONDITIONS

All laboratory experiments were conducted using a mercury vapor "H" bulb. A broad spectrum UV source is strongly recommended. A tack-free surface requires 1-2 seconds exposure at a minimum of 500 mW/cm² (UVA) or 3-5 seconds at a minimum of 250 mW/cm² (UVA). Note, longer exposure times are required for lower intensity lamp conditions.

LED UV lamp systems may provide sufficient cure if the output wavelength is near 365 nm and a high power source is used. Users are responsible to test and validate cure efficacy.

PRODUCT SPECIFICATIONS*

Physical Property	Test Method	Performance Range
Form		Flowable
Cure Chemistry		UV Only
Shadow Area Cure		No
Appearance		Clear
UV Indicator		No
Viscosity (cPs)	Brookfield RV #5 @ 20 rpm	18,000

TYPICAL CURED PROPERTIES*

Physical Property	Test Method	Typical Value
Specific Gravity	ASTM D1875	0.97
Durometer (Shore A)	ASTM D2240	5
Durometer (Shore 00)	ASTM D2240	54
Tensile Strength (psi)	ASTM D412	24
Elongation (%)	ASTM D412	260

ELECTRICAL PROPERTIES*

Electrical Property	Test Method	Typical Value
Dielectric Strength	ASTM D149	14.38 kV/mm 365 V/mil
Dielectric Constant at 100 Hz	ASTM D150	3.35
Dielectric Constant at 100 kHz	ASTM D150	3.33
Dissipation Factor at 100 Hz	ASTM D150	0.0012
Dissipation Factor at 100 kHz	ASTM D150	0.0014
Volume Resistivity (Ω cm)	ASTM D257	1.66 x 10 ¹²

* The values outlined reflect testing that was conducted under laboratory conditions, actual results may vary. Results are after UV cure.

(continued on page 2)

Depth of Cure

UV curable silicones require UV waves to penetrate the silicone in order to initiate cure. Therefore, depth of cure is limited by UV wave transmittance. Most of our UV cure silicones can be sufficiently cured to depths of 3/4" to 1" (19 mm to 25 mm) depending on formulation ingredients.

TYPICAL SURFACE PREPARATION

Novagard 800 Series 800-620 can be applied to cleaned and "no clean" surfaces. It is recommended to test this product for compatibility with all contact surfaces.

Clean Up

Common solvents such as isopropyl alcohol (IPA), odorless mineral spirits (OMS), or acetone can be used to help with cleanup of uncured silicone. For cured silicone, soften the silicone first with solvent and then brush or scrape away.

Repairability

Novagard UV curable silicone conformal coatings and sealants are repairable and can be removed from substrates and circuitry by scraping or cutting. Additionally, one can use solvents to swell the silicone making it much easier to scrape or brush away from the surface. This method can be used for circuit boards where a component requires replacement. Once a component is replaced, fresh silicone can be brushed or poured on the bare component and then cured.

ADDITIONAL INFORMATION

Useful Temperature Ranges

Silicones withstand extreme high and low temperatures with little to no property change due to its non-reactive and stable structure. Most Novagard silicones have an operational temperature range of -40°C to 200°C (-40°F to 257°F) for long periods of time. This can vary, however, depending on formulation, configuration, and stress sensitivity of components in the application, in addition to cooling rates, hold times, and prior temperature history.

Novagard believes that the information provided is a true and accurate description of the typical characteristics of the aforementioned product; however, it is the responsibility of the individual user to thoroughly test the product in their specific application to determine performance, efficacy, and safety.

PACKAGING

Novagard 800 Series 800-620 is available in 310 ml cartridges (10.3 ounce), 5 gallon pails, and 55 gallon drums. Samples are typically provided in 30 cc hybrid syringes although larger sample sizes may be an option. If you require a different package size for a long-term commercial purchase, contact your Novagard representative.

STORAGE AND SHELF LIFE

Novagard 800 Series 800-620 when stored in its original, unopened container at or below 80°F is usable for up to twelve (12) months. Refrigeration down to 3°C may prolong the shelf life of the material in unopened, original packaging, and usefulness must be determined by the end user.

CUSTOMIZATION

As the largest R&D group in our class, we have significant expertise and experience in a wide array of technical disciplines. Our team includes experienced Ph.D. scientists and engineers along with subject matter experts who can customize our family of UV and UV dual cure silicone products to fit your exact needs.

Any of our UV or UV dual cure silicone products may be modified with adhesion promoters designed for specific substrates, even low-energy substrates like polyethylene terephthalate (PET). In addition to modifying adhesion profiles of any of our UV or UV dual cure silicone products, we can also adjust any of the following physical properties as needed:

Uncured:	Cured:
• Viscosity	• Shore hardness
• Thixotropy	• Tensile strength
• Pot life	• Adhesion
• UV tracer	• Elongation

Contact us at (216) 881-8111 or products@novagard.com. We'd be happy to discuss your specific project.

COMPLIANCE INFORMATION

Novagard 800 Series 800-620 does not contain any substances included on the most recent published REACH "Candidate List of Substances of Very High Concern".

Novagard 800 Series 800-620 does not contain any chemicals on the Prop65 list at a level requiring special labeling.

PRECAUTIONS

Consult and obey all applicable local, state, and federal regulations for disposal of solvent and silicone waste. For additional information consult product safety data sheet (SDS).