

NOVAFLEX^{SILICONE}

Metal Roof & Panel Adhesive Sealant



- Neutral cure silicone
- Excellent adhesion
- Permanently flexible
- Extrudes to -20°F
- Adheres to:
 - Metals
 - Wood
 - Masonry
 - PVC/PVDF
 - Common Construction Materials
- Also used as
 - Gutter Sealant
 - Chimney Flashing
 - Snow Guard
 - Pipe Boots



MR102
STONE WHITE



MR3010
REGAL WHITE




MR3010
BONE WHITE




MR3404
SANDSTONE




MR3461
ALMOND




MR115
BRIGHT SILVER




MR3333
SIERRA TAN




MR3421
CHAMPAGNE




MR3514
DOVE GRAY



MR4103
SILVERSMITH




MR3201
BRIGHT
COPPER




MR184
TERRA COTTA




MR196
BANNER RED




MR182
COLONIAL RED



MR180
BRANDYWINE



MR3823
SLATE BLUE




MR171
REGAL BLUE



MR197
PATINA GREEN




MR169
CLASSIC
GREEN




MR3775
TEAL




MR168
HARTFORD
GREEN




MR117
SLATE GRAY




MR117
PEWTER




MR134
CHARCOAL




MX3204
MEDIUM
BRONZE




MR194
DARK
BRONZE



MR131
EXTRA DARK
BRONZE



MR131
MANSARD
BROWN



MR110
MATTE BLACK

NOVAFLEX

Metal Roof & Panel Adhesive Sealant

Product Specifications

Physical Property	Test Method	Performance Range Type I - Class 35	Performance Range Type II - Class 50
Appearance		Paste (Various Colors)	Paste (Various Colors)
Viscosity	Brookfield #7 @10 rpm	3,500-7,000 poises	4,500-8,000 poises
Extrusion Rate	1/8" Orifice @ 50 psi	30 - 80 grams/minute	30 - 80 grams/minute
Skin Over Time	3/8" @ 50% RH & 77°F	5 - 10 minutes	5 - 10 minutes
Through Cure	3/8" @ 50% RH & 77°F	48 hours (14 days for OEM window applications)	48 hours (14 days for OEM window applications)

Typical Properties*

Physical Property	Test Method	Typical Value Type I - Class 35	Typical Value Type II - Class 50
Specific Gravity		1.00 - 1.05	1.15 - 1.25
Tensile Strength	ASTM D412	140 - 200 psi	170 - 220 psi
Elongation	ASTM D412	500 - 650%	800 - 1000%
Tear Resistance	ASTM D624	30 - 35 pli	30 - 35 pli
Shore Hardness	ASTM D2240	20 +/- 5	25 +/- 5
Service Temperature		- 40°F to 400°F (- 40°C to 204°C)	- 40°F to 400°F (- 40°C to 204°C)
Joint Sealant Designation	ASTM C920	Type S Grade NS Class 35 Use NT, M, G, A, O	Type S Grade NS Class 50 Use NT, M, G, A, O
Adhesion Glass Aluminum Vinyl	ASTM D903	12 - 15 pli 10 - 14 pli 12 - 15 pli	12 - 15 pli 10 - 14 pli 12 - 15 pli

*The values outlined reflect testing that was conducted under laboratory conditions, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional information.



- Neutral cure silicone
- Excellent adhesion
- Permanently flexible
- Extrudes to -20°F
- Adheres to:
 - Metals
 - Wood
 - Masonry
 - PVC/PVDF
 - Common Construction Materials
- Also used as
 - Gutter Sealant
 - Chimney Flashing
 - Snow Guard
 - Pipe Boots

Permanently Flexible

- Will not shrink or crack
- Waterproof
- Mold/Mildew resistant
- Superior UV resistance

Interior and Exterior Applications

- Excellent adhesion to most building substrates
- Completely cured within 48 hours
- Will not sag or slump
- Tack-free in 10 minutes

Easily Gunned at all Temperatures

- Weatherproof plastic cartridges with removable tips
- Excellent tooling properties

VOC Compliant in all 50 States (Green Building Compliant)

- Low odor
- Solvent free

AAMA Verified for Window Installs

- Will not freeze
- Available in all major siding, trim coil, window, and metal roof manufacturer colors
- 18 month shelf life

Professional Grade

NOVAGARD

5109 Hamilton Avenue, Cleveland, OH 44114 USA
 (216) 881-8111 | (800) 380-0138 | (216) 881-6977 F
 novagard.com

ISO 9001:2015 QMS (with Design), IATF 16949:2016 QMS (with Design)
 Certified Women's Business Enterprise



NovaFlex is proudly made in Cleveland, OH
 Effective Date: Dec 2022-v1.4