

NOVAFLEX

Metal Roof & Panel Adhesive Sealant



- Excellent adhesion
- Permanently flexible
- Extrudes to -20°F
- Adheres to:
 - Vinyl Siding
 - Fiber Cement Siding
 - Metals
 - Wood
 - Masonry
 - PVC
 - PVDF
 - Common Construction Materials



MR101
PURE WHITE



MR3561
BONE WHITE



MX3473
IVORY




MR3461
STONE



MR3412
SIERRA TAN




MR3514
LIGHT GRAY



MR4103
GALVALUME



MX3301
CLAY



MX141
BUCKSKIN



MR3201
COPPER METALLIC



MR3823
HAWAIIAN BLUE



MR171
GALLERY BLUE



MR197
PATINA GREEN




MX3711
FOREST GREEN




MX3570
GRANITE FROST




MR196
BRIGHT RED



MR189
DARK RED



MR182
BARN RED



MR180
BURGUNDY




MR193
BROWN




MR127
COUNTY CHARCOAL



MR121
BRONZE



MR123
MIDNIGHT FROST



MR110
BLACK

Metal Roof & Panel Adhesive Sealant Multi-Purpose Adhesive Sealant

Novagard offers a complete line of **installation sealants**



Metal Roof & Panel Adhesive Sealant

Multi-Purpose Adhesive Sealant

Gutter Seal (paste & flowable)

Hybrid Construction Sealant

Textured Hybrid Construction Sealant

Silicone Tile Adhesive & Grout

Expansion Joint Sealant

Pitch Pocket Penetration Sealant

Fibered Roof Mastic

Butter Grade Mastic

Metal Roof Repair & Patch Mastic

NOVAGARD

5109 Hamilton Avenue, Cleveland, OH 44114 USA
(216) 881-8111 | (800) 380-0138 | (216) 881-6977 F
novagard.com

ISO 9001:2015 QMS (with Design), IATF 16949:2016 QMS (with Design)
Certified Women's Business Enterprise

PRODUCT SPECIFICATIONS			
Physical Property	Test Method	Performance Range Type I - Class 35	Performance Range Type II - Class 50
Appearance		Paste (Various Colors)	Paste (Various Colors)
Viscosity	Brookfield #7 @10 rpm	3,500-7,000 poises	4,500-8,000 poises
Extrusion Rate	1/8" Orifice @ 50 psi	30 - 80 grams/minute	30 - 80 grams/minute
Skin Over Time	3/8" @ 50% RH & 77°F	5 - 10 minutes	5 - 10 minutes
Through Cure	3/8" @ 50% RH & 77°F	48 hours (14 days for OEM window applications)	48 hours (14 days for OEM window applications)

TYPICAL PROPERTIES*			
Physical Property	Test Method	Typical Value Type I - Class 35	Typical Value Type II - Class 50
Specific Gravity		1.00 - 1.05	1.15 - 1.25
Tensile Strength	ASTM D412	140 - 200 psi	170 - 220 psi
Elongation	ASTM D412	500 - 650%	800 - 1000%
Tear Resistance	ASTM D624	30 - 35 pli	30 - 35 pli
Shore Hardness	ASTM D2240	20 +/- 5	25 +/- 5
Service Temperature		- 40°F to 400°F (- 40°C to 204°C)	- 40°F to 400°F (- 40°C to 204°C)
Joint Sealant Designation	ASTM C920	Type S Grade NS Class 35 Use NT, M, G, A, O	Type S Grade NS Class 50 Use NT, M, G, A, O
Adhesion Glass Aluminum Vinyl	ASTM D903	12 - 15 pli 10 - 14 pli 12 - 15 pli	12 - 15 pli 10 - 14 pli 12 - 15 pli

*The values outlined reflect testing that was conducted under laboratory conditions, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional information.

Permanently Flexible

- Will not shrink or crack
- Waterproof
- Mold/Mildew resistant
- Superior UV resistance

Interior and Exterior Applications

- Excellent adhesion to most building substrates
- Completely cured within 48 hours
- Will not sag or slump
- Tack-free in 10 minutes

Easily Gunned at all Temperatures

- Weatherproof plastic cartridges with removable tips
- Excellent tooling properties

VOC Compliant in all 50 States (Green Building Compliant)

- Low odor
- Solvent free

AAMA Verified for Window Installs

- Will not freeze
- Available in all major siding, trim coil, window, and metal roof manufacturer colors
- 18 month shelf life

Professional Grade



Proudly made in Cleveland, OH
Effective Date: Mar 2023-v1.2