



A NEW PLAYER
IN SEALANTS IS
COMING AT YOU
REAL FAST.

NOVA**GARD**

AND WE'LL MAKE A BIG IMPACT ON YOUR BUILD.

This 'new' player happens to have over 40 years experience formulating sealants and adhesives. Now - along with our proven products, people, and technical prowess - Novagard has a new purpose:

To stand out and make a real dent in the Transportation Manufacturing Industry.

We assembled the largest R&D team of a company our size. Then put together the lineup of products you'll see inside. And we're ready, excited, and way more than willing to help you take on any manufacturing challenge.

Give us the chance. We promise, you'll love the change.

NOVAGARD



Replace

SIKA 221, 227, 505UV
MANUS 75am, 77am
with



GENERAL PURPOSE

A high-performance sealant that provides a permanent, elastic bond to fasten materials. Ideal for sealing materials with dissimilar coefficients of expansion. Paintable after 1 hour.

APPEARANCE	Paste Black, Gray, White
VISCOSITY (POISES)	-
SKIN OVER TIME 3/8" @ 50% RH & 77°F	10 - 25 min
THROUGH CURE 3/8" @ 50% RH & 77°F	7 days
SPECIFIC GRAVITY	1.45 - 1.55
TENSILE STRENGTH ASTM D412	225 - 250 psi
ELONGATION ASTM D412	350 - 400%
SHORE HARDNESS ASTM D2240	45 +/- 5
ADHESION ASTM D903	
GLASS	13 pli
ALUMINUM	15 pli
WOOD	15 pli
PVC	14 pli
JOINT MOVEMENT ASTM C719	+/- 25
UV EXPOSURE ASTM G154 (2,000 hours UV-A)	Pass
PACKAGING	cartridges, sausage packs, pails, and drums

Replace

MANUS 76am
with



SEMI SELF-LEVELING

A controlled flow, semi self-leveling sealant suitable for sealing roofing components and mechanically fixed joints. Paintable after 1 hour.

APPEARANCE	Viscous Fluid Black, Gray, White
VISCOSITY (POISES)	-
SKIN OVER TIME 3/8" @ 50% RH & 77°F	10 - 25 min
THROUGH CURE 3/8" @ 50% RH & 77°F	7 days
SPECIFIC GRAVITY	1.45 - 1.55
TENSILE STRENGTH ASTM D412	175 - 225 psi
ELONGATION ASTM D412	250 - 300%
SHORE HARDNESS ASTM D2240	45 +/- 5
ADHESION ASTM D903	
GLASS	13 pli
ALUMINUM	15 pli
WOOD	15 pli
PVC	14 pli
JOINT MOVEMENT ASTM C719	+/- 25
UV EXPOSURE ASTM G154 (2,000 hours UV-A)	Pass
PACKAGING	cartridges, sausage packs, pails, and drums

Get the very best

balanced blend
from



BALANCED PERFORMANCE

A single-component, non-corrosive hybrid offering excellent balance between cure rate, adhesion, and physical properties. Great for bonding dissimilar materials and creating formed-in-place gaskets. Paintable after 1 hour.

APPEARANCE	Paste White
VISCOSITY (POISES)	≥3,000
SKIN OVER TIME 3/8" @ 50% RH & 77°F	15 - 45 min
THROUGH CURE 3/8" @ 50% RH & 77°F	7 days
SPECIFIC GRAVITY	1.4 - 1.5
TENSILE STRENGTH ASTM D412	300 psi
ELONGATION ASTM D412	300%
SHORE HARDNESS ASTM D2240	45 +/- 5
ADHESION ASTM D903	
GLASS	13 pli
ALUMINUM	15 pli
WOOD	15 pli
PVC	14 pli
JOINT MOVEMENT ASTM C719	+/- 35
UV EXPOSURE ASTM G154 (2,000 hours UV-A)	Pass
PACKAGING	cartridges, sausage packs, pails, and drums

Replace
SIKA 552 and 252
 MANUS 25am
 with



HEAVY-DUTY FASTENING

For bonding in one step. The remarkable adhesive can replace rivets, screws, welds, and other mechanical fasteners. Extremely peel and tear resistant. Paintable after 1 hour.

Homologación por CESVI MEXICO

APPEARANCE	Paste Black, White
VISCOSITY (POISES)	4,500 - 8,000
SKIN OVER TIME 3/8" @ 50% RH & 77°F	15-25 min
THROUGH CURE 3/8" @ 50% RH & 77°F	4 days
SPECIFIC GRAVITY	1.25 - 1.40
TENSILE STRENGTH ASTM D412	430-480 psi
ELONGATION ASTM D412	750-800%
SHORE HARDNESS ASTM D2240	40 +/- 5
ADHESION ASTM D903 GLASS ALUMINUM WOOD	12-16 pli 12-16 pli 12-16 pli
JOINT MOVEMENT ASTM C719	+/- 50
UV EXPOSURE ASTM G154 (2,000 hours UV-A)	Pass
PACKAGING	cartridges, sausage packs, pails, and drums

Nothing is
 stronger
 than



HIGH TENSILE

Extremely high tensile rate for superior adhesion without a primer, at a superior cure rate. Typically used to bond dissimilar materials and a multitude of other applications. Paintable after 1 hour.

APPEARANCE	Paste Black, White
VISCOSITY (POISES)	4,500 - 8,000
SKIN OVER TIME 3/8" @ 50% RH & 77°F	15-25 min
THROUGH CURE 3/8" @ 50% RH & 77°F	4 days
SPECIFIC GRAVITY	1.35 - 1.40
TENSILE STRENGTH ASTM D412	750 psi
ELONGATION ASTM D412	220%
SHORE HARDNESS ASTM D2240	45 +/- 5
ADHESION ASTM D903 GLASS ALUMINUM WOOD	12-16 pli 12-16 pli 12-16 pli
JOINT MOVEMENT ASTM C719	n/a
UV EXPOSURE ASTM G154 (2,000 hours UV-A)	Pass
PACKAGING	cartridges, sausage packs, pails, and drums



PUT US TO THE TEST.

Give us your biggest problem, along with two square feet of your substrate, and we'll let you know if we can do a better job on your application than the product you're already using.

Honestly, you've got nothing to lose.

Except, perhaps, that nagging doubt you're not getting the best performance at the best price.

Call now to arrange for your free test.

Punch 1 (800) 380-0138
and say to whomever answers,
*"I work in the Transportation
Manufacturing Industry and
I want to put your products to the test."*
They'll be very happy to assist you.

NOVAGARD



VOC
COMPLIANT
ENVIRONMENTALLY
RESPONSIBLE



Need a seal that also cushions?

Our Foam Seal custom-engineered PVC foam and foam tapes offer strength and durability, plus economy. They outperform more expensive alternatives, giving design engineers all the performance they need while simultaneously managing costs.

FOAMSEAL
by Novagard



NOVAGARD
SILICONE | HYBRIDS | FOAM

5109 Hamilton Avenue, Cleveland, OH 44114 USA
(216) 881-8111 | (800) 380-0138 | (216) 881-6977 fax | novagard.com

ISO 9001:2015 QMS (with design), IATF 16949:2016 QMS (with design)
Certified Women's Business Enterprise | Certified Woman Owned Small Business