



Easy to gun
and tool



Paintable
in 30 min



UV
resistant



No solvents
or odor



All weather



Safe for
indoor/outdoor



Permanently
flexible



24 month
shelf life



Standard
Colors



NOVA BOND PRO

PREMIUM HYBRID SEALANT



NBX100
White




NBX105
Antique White



NBX107
Cream




NBX145
Canvas



NBX140
Beige




NBX3431
Cobblestone




NBX146
Sandstone



NBX134
Terratone



NBX120
Dark Bronze



NBX110
Black

Visit novagard.com/colors to use our online matching tool
to cross reference NovaBond colors to popular manufacturers.

Cured NovaFlex dots are shown for color purposes only. Ask your rep if you require a NovaBond Pro sample.

NOVABOND[®] PRO

PREMIUM HYBRID SEALANT



PRODUCT SPECIFICATIONS

Physical Property	Test Method	Performance Range
Appearance		Paste (Various Colors)
Viscosity	Brookfield #7 @ 10 rpm	2,000 - 7,000 poises
Extrusion Rate	1/8" Orifice @ 50 psi	≥50 grams/minute
Skin Over Time	3/8" @ 50% RH & 77°F	10 - 30 minutes

*The values outlined reflect testing that was conducted under laboratory conditions, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional info.

Made to Order
Colors



NBX3020
Arctic White



NBX3515
Cape Cod Gray



NBX159
Limestone



NBX182
Red Rock



NBX168
Forest Green



NBX194
Exterior Bronze



NBX193
Cocoa Bean

TYPICAL PROPERTIES*

Physical Property	Test Method	Typical Value
Specific Gravity		1.40 - 1.50
Tensile Strength	ASTM D412	200 - 325 psi
Elongation	ASTM D412	250 - 475%
Hardness (Shore A)	ASTM D2240	45 - 55
Through Cure	3/8" @ 50% RH & 77°F	7 days
Service Temperature		-40°F to 176°F (-40°C to 80°C)
Application Temperature		-10°F to 122°F (-23°C to 50°C)
Adhesion Glass Aluminum Wood PVC PVDF Concrete	ASTM C794	>15 pli >20 pli >15 pli >15 pli >25 pli >15 pli
Joint Movement	ASTM C719	+/- 35
UV Exposure	ASTM G154 (2,000 hours UV-A)	Pass
Shelf Life		24 months

Effective Date: Mar 2025-v1.6