



UV resistant



No solvents or odor



All weather



Safe for indoor/outdoor



Permanently flexible



Paintable in 30 min



24 month shelf life



Standard Colors



# NOVABOND PRO


## PREMIUM HYBRID SEALANT




NBX100  
White




NBX105  
Antique White



NBX107  
Cream



NBX145  
Canvas



NBX140  
Beige




NBX3431  
Cobblestone




NBX146  
Sandstone



NBX134  
Terratone



NBX120  
Dark Bronze



NBX110  
Black

Visit [novagard.com/colors](http://novagard.com/colors) to use our online matching tool to cross reference NovaBond colors to popular manufacturers.

# NOVABOND PRO

## PREMIUM HYBRID SEALANT



### PRODUCT SPECIFICATIONS

Physical Property	Test Method	Performance Range
Appearance		Paste (Various Colors)
Viscosity	Brookfield #7 @ 10 rpm	2,000 - 7,000 poises
Extrusion Rate	1/8" Orifice @ 50 psi	≥50 grams/minute
Skin Over Time	3/8" @ 50% RH & 77°F	10 - 30 minutes
Shelf Life		24 months

\*The values outlined reflect testing that was conducted under laboratory conditions, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional info.

### TYPICAL PROPERTIES\*

Physical Property	Test Method	Typical Value
Specific Gravity		1.40 - 1.50
Tensile Strength	ASTM D412	200 - 325 psi
Elongation	ASTM D412	250 - 475%
Hardness (Shore A)	ASTM D2240	45 - 55
Through Cure	3/8" @ 50% RH & 77°F	7 days
Service Temperature		-40°F to 176°F (-40°C to 80°C)
Application Temperature		-10°F to 122°F (-23°C to 50°C)
Adhesion Glass Aluminum Wood PVC PVDF Concrete	ASTM C794	>15 pli >20 pli >15 pli >15 pli >25 pli >15 pli
Joint Movement	ASTM C719	+/- 35
UV Exposure	ASTM G154 (2,000 hours UV-A)	Pass

Effective Date: Oct 2024-V1.4

Made to Order  
Colors



NBX3020  
Arctic White



NBX3515  
Cape Cod Gray



NBX159  
Limestone



NBX182  
Red Rock



NBX168  
Forest Green



NBX194  
Exterior Bronze



NBX193  
Cocoa Bean