

NOVAFLASH™

MXB Butter Grade Mastic

NovaFlash Butter Grade Mastic is an exceptionally versatile, tough yet flexible mastic and roof sealer designed for use on a variety of membranes and coated roofs. The product can be applied with a trowel for high-build applications or a stiff-bristled brush for low-build applications. NovaFlash Butter Grade Mastic cures quickly and provides immediate waterproofing for short-term, long-term, and emergency repairs.



- 100% silicone rubber
- Excellent repair material for many roofing substrates
- Rain safe in 1 hour (70°F/50% RH)
- Excellent adhesion and hang
- Easily applied by trowel or stiff-bristled brush on vertical or horizontal surfaces
- Solvent-free
- VOC compliant
- Resistant to ponding water
- No hardening, chalking, crazing, or cracking
- Wide temperature application range: -20°F to 160°F (-29°C to 71°C)
- Wide temperature performance range: -40°F to 400°F (-40°C to 204°C)



Typical uses include: Rough areas of SPF, drain bowls, and under and around rooftop-mounted equipment. It is also an excellent repair material for direct-to-metal repairs, spray polyurethane foam, smooth built-up, smooth modified bitumen, granulated modified bitumen, aged single ply roof membrane, flashings, fasteners and drains.

Shelf Life: 18 months from date of manufacture when stored unopened in a cool and shaded location.

Packaging Information: NovaFlash Butter Grade Mastic is available in 1 gallon pails.

Specifications: Meets or exceeds the requirements of California Proposition 65. 50-state VOC Compliant. REACH Compliant.

Disposal: Consult and obey all applicable local, state, and federal regulations. For additional information, consult product Safety Data Sheet.

Precautions: Do not use in, or around, highly oxidative chemicals such as liquid oxygen, chlorine, or peroxides.



Made in USA. Professional Grade.

NOVAFLASH

MXB Butter Grade Mastic

APPLICATION INFORMATION

Clean: Surface must be clean and free of all dust, rust, residues, foreign matter, and all contaminants (chalk, grease, wax, etc.) that may cause loss of adhesion. Remove rust and scale from metal by wire brushing. Sweep area thoroughly to remove all dust, dirt, and other foreign matter that would interfere with a good bond. Scrub accumulated residue on low areas with detergent and rinse thoroughly. Surface must be dry and frost-free. Sealant adhesion should be tested on each different substrate prior to use. To test adhesion, apply sealant and allow to cure thoroughly. Then, pull one end to test adhesion strength.

Apply: Repair cracks, breaks, tears, and holes by applying 1/8" to 1/2" thick with a trowel, putty knife, or stiff-bristled brush. Thicker application results in better performance and longer sealant life. Sealant can be applied over old silicone coating or sealant which has cured (following cleaning instructions above). Work the sealant into the damaged area and spread it 2" to 4" beyond, feathering the edges. Check to see that no voids have been left in patched areas. If so, apply more sealant and allow to set up before coating. NovaFlash Butter Grade Mastic is tack-free in about 1 hour and fully cured in about 48 hours (dependent on weather conditions, such as temperature and humidity). Not recommended for application at temperatures below 10°F or if rain is expected within 1 hour of application. DO NOT THIN.

Keep container covered and sealed. Material left exposed to the atmosphere may begin to cure and form a skin on the surface. If this occurs, remove the skin and use the rest. DO NOT MIX PRODUCT.

| PRODUCT SPECIFICATIONS | | |
|------------------------|----------------------|-------------------------------|
| Physical Property | Test Method | Performance Range |
| Appearance | | Mastic Paste (Various Colors) |
| Skin Over Time | 3/8" @ 50% RH & 77°F | 5 - 15 minutes |
| Through Cure | 3/8" @ 50% RH & 77°F | 48 hours |

| TYPICAL PROPERTIES* | | |
|--------------------------|-------------|----------------------------|
| Physical Property | Test Method | Typical Value |
| Specific Gravity | | 1.25 - 1.55 |
| Tensile Strength | ASTM D412 | 120 - 170 psi |
| Elongation | ASTM D412 | 500 - 700% |
| Shore Hardness | ASTM D2240 | 20 minimum |
| Tear Resistance | ASTM D624 | 30 - 35 pli |
| Adhesion Metal SPF | ASTM D903 | 10 - 14 pli 10 - 14 pli |

*The values outlined reflect testing that was conducted under laboratory conditions, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional info.

| COVERAGE | |
|-----------|---------------|
| Thickness | Coverage Area |
| 1/16" | 24 sq ft |
| 1/8" | 12 sq ft |
| 1/4" | 6 sq ft |

Clean-up: Clean hands with waterless hand cleaner. Equipment may be cleaned before sealant cures with mineral spirits.

Professional Grade



SILICONE | HYBRIDS | FOAM

5109 Hamilton Avenue, Cleveland, OH 44114 USA
(216) 881-8111 | (800) 380-0138 | (216) 881-6977 F
novagard.com

ISO 9001:2015 QMS (with Design) | IATF 16949:2016 QMS (with Design)
Certified Women's Business Enterprise | Certified Woman Owned Small Business

Effective Date: Mar 2021-v1.6

Carry our
complete family
of roofing sealants



Proudly made in Cleveland, Ohio