



## NOVABOND<sup>®</sup> Hybrid Construction Sealant




NBP100  
White  
91017



NBP107  
Colonial White  
91013



NBP146  
Stone  
91015



NBP3515  
Limestone  
91016



NBP120  
Medium Bronze  
107777



NBP194  
Dark Bronze  
91014

Colors shown for illustrative purposes. Verify product color match before applying.

- Excellent adhesion
- Permanently flexible
- Paintable in 1 hour
- Extrudes down to -10°F
- Adheres to:
  - Metal
  - Wood
  - Masonry
  - PVC
  - PVDF
  - Asphalt Shingles
  - Common Construction Materials



Novagard offers a complete line of **installation sealants**

**Metal Roof & Panel Adhesive Sealant**

**Multi-Purpose Adhesive Sealant**

**Gutter Seal (paste & flowable)**

**Hybrid Construction Sealant**

**Textured Hybrid Construction Sealant**

**Tub Surround Sealant & Tile Grout**

**Expansion Joint Sealant**

**Pitch Pocket Penetration Sealant**

**Fibered Roof Mastic**

**Butter Grade Mastic**

**Metal Roof Repair & Patch Mastic**

**NOVAGARD**

5109 Hamilton Avenue, Cleveland, OH 44114 USA  
(216) 881-8111 | (800) 380-0138 | (216) 881-6977 F  
novagard.com

ISO 9001:2015 QMS (with Design), IATF 16949:2016 QMS (with Design)  
Certified Women's Business Enterprise

**NOVABOND**  
Hybrid Construction Sealant



PRODUCT SPECIFICATIONS		
Physical Property	Test Method	Performance Range
Appearance		Paste (Various Colors)
Viscosity	Brookfield #7 @ 10 rpm	≥ 3,000 poises
Extrusion Rate	1/8" Orifice @ 50 psi	≥ 50 grams/minute
Skin Over Time	3/8" @ 50% RH & 77°F	10 - 45 Minutes
Through Cure	3/8" @ 50% RH & 77°F	7 days

TYPICAL PROPERTIES*		
Physical Property	Test Method	Typical Value
Specific Gravity		1.40 - 1.50
Tensile Strength	ASTM D412	200 psi
Elongation	ASTM D412	300%
Shore A Hardness	ASTM D2240	45+/- 5
Service Temperature		-30°F to 200°F (-34°C to 93°C)
Application Temperature		-10°F to 160°F (-23°C to 71°C)
Adhesion Glass Aluminum Wood PVC	ASTM D903	13 pli 15 pli 15 pli 14 pli

\*The values outlined reflect testing that was conducted under laboratory conditions, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional info.

**Paintable in 1 Hour**

- Permanently flexible
- Will not shrink or crack
- Waterproof
- Mold/Mildew resistant
- UV resistant

**Interior and Exterior Applications**

- Excellent adhesion to most building substrates
- Completely cured within 5-7 days
- Will not sag or slump
- Tack-free in 10-45 minutes

**Easily Gunned at all Temperatures**

- Weatherproof plastic cartridges with removable tips
- Excellent tooling properties

**VOC Compliant in all 50 States (Green Building Compliant)**

- California Proposition 65 Compliant
- Low odor
- Solvent free

**AAMA Verified for Window Installs (smooth paste)**

- Available in all major siding, trim coil, and window manufacturer colors
- Will not freeze

**Professional Grade**



Proudly made in Cleveland, OH  
Effective Date: Aug 2023-v1.0