

**Novagard® 600 Series 600-170
Potting and Encapsulant
Specification Data**



DESCRIPTION

Novagard 600 Series 600-170 is a two-component silicone that, when mixed, cures to a moderately flexible elastomer. This material is ideally suited for application as a general potting compound in power supplies, connectors, and junction boxes.

FEATURES

- Low shrinkage
- No exotherm during cure
- Low viscosity
- Excellent dielectric properties
- No solvents or cure by-products
- No post cure required
- UL rated (pending)

INSTRUCTIONS

This material is shipped in separate containers that are labeled Part A and Part B. While the material may be mixed by hand, it is more appropriate to use automated, meter-mixing equipment as the work life is extremely short and the ultimate cure time is exceedingly fast. The compound is designed with a 1:1 volume:volume mix ratio. Automated mixing equipment eliminates the need for a deaeration cycle. If mixing by hand, weigh 50 parts of Part A into an appropriately sized mixing vessel; add 50 parts of Part B and mix thoroughly.

STORAGE

Novagard 600 Series 600-170 may be stored in the original unopened containers at, or below, 80°F (25°C) for up to one year.

AVAILABILITY

Novagard 600 Series 600-170 is available in 5 gallon, straight-sided pails, or 55 gallon drums.

PRECAUTIONS

Certain materials, chemicals, curing agents, and plasticizers may inhibit the cure. The most notable are organo-tin catalysts, amino compounds, polysulfide, and other sulfur-containing materials.

Do not use in or around highly oxidative chemicals such as liquid oxygen, chlorine, or peroxides. Not recommended for surfaces that are to be painted.

GENERAL PROPERTIES

BEFORE CURE

Physical Property	Test Method	Performance Range
Appearance	After mixing	Black
Mix Ratio	Base:Cure (by volume)	1:1
Specific Gravity	Mixed, 25°C Part A Part B	1.35 – 1.45 1.35 – 1.45
Viscosity	Mixed, 25°C Part A Part B	6,000 – 8,500 cPs 18,000 – 22,000 cPs
Working Time	Mixed, 25°C	<15 minutes
Cure Time	25°C	2 – 3 hours

AFTER CURE (7 Days at 25°C/50% RH)*

Physical Property	Test Method	Typical Value
Tensile Strength	ASTM D412	400 - 700 psi
Elongation	ASTM D412	100 - 300%
Shore A	ASTM D2240	45 - 65
Tear Resistance	ASTM D624	15 – 25 pli
Flammability Class	UL 94	V0 (Pending)
Volume Resistivity	ASTM D257	8.45 x 10 ¹³ Ω-cm
Dissipation Factor (100 Hz/100 kHz)	ASTM D150	0.0020/0.0017
Dielectric Constant (100 Hz/100 kHz)	ASTM D150	3.69/3.71
Dielectric Strength (10 mil gap)	ASTM D149	470 v/mil

*The values outlined reflect testing that was conducted under laboratory conditions, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional information.

ADDITIONAL INFORMATION

Novagard believes that the information provided is a true and accurate description of the characteristics of the aforementioned product, however, it is the responsibility of the individual user to thoroughly test the product in their specific application to determine performance, efficacy, and safety.